

ACCEPTANCE OF METALLIC MATERIALS USED FOR PRODUCTS IN CONTACT WITH DRINKING WATER

4MS Common Approach

Part A – Procedure for the acceptance

Part B – 4MS Common Composition List

Adopted by the 4MS Joint Management Committee

10th Revision:

19th June 2018

France, Germany, the Netherlands and the United Kingdom (4MS) work together in the framework of the 4MS Common Approach as laid down in the Declaration of Intent (January 2011). This common approach aims for convergence of the respective national approval schemes for materials and products in contact with drinking water.

The 4MS have adopted Part A of this document as a common basis for implementing the concept of accepting metallic materials in their national regulations. The document is subject to revisions agreed by the 4MS.

Part B of this document includes a Composition List of metallic materials accepted in all of the 4MS following the procedure described in Part A.

Further information may be obtained from any of the competent authorities of the 4MS.

Bundesministerium für Gesundheit (Deutschland)

Ministère du Travail, de l'Emploi et de la Santé (France)

Ministerie van Infrastructuur en Milieu (Nederland)

Department for Environment, Food and Rural Affairs (United Kingdom)

Part B – 4MS Common Composition List

Table of contents

1	INTRODUCTION.....	5
2	COMPILATION OF A COMMON COMPOSITION LIST	5
3	STRUCTURE OF THE COMPOSITION LIST (SEE PART A 3.2).....	5
I	COPPER ALLOYS.....	8
1	Copper-zinc alloys	8
2	Copper-zinc-aluminum alloys.....	11
3	Copper-zinc-aluminum-tin alloys	12
4	Copper-zinc-arsenic alloys	13
5	Copper-zinc-arsenic-aluminium alloys	14
6.	Copper-zinc-arsenic-antimony-aluminum alloys	15
7	Copper-zinc-lead alloys	16
8	Copper-zinc-lead-aluminium alloys	18
9	Copper-zinc-lead-arsenic-aluminium alloys.....	19
10	Copper-zinc-lead-arsenic-antimony-aluminum alloys	21
11	Copper-zinc-lead-arsenic-aluminium-silicon alloys.....	22
12	Copper-tin-zinc-lead-nickel alloys.....	23
13	Copper-tin-zinc-phosphorous-sulphur alloys	24
14	Copper-zinc-silicon-phosphorous alloys	25
15	Copper-silicon-zinc-manganese-phosphorous alloys.....	27
16	Copper-tin-phosphorous alloys	29
17	Copper-tin-lead-phosphorous alloys	30
18	Copper alloys for product group D	31
II	COPPERS.....	32

1 Copper	32
2 Tinned copper pipes and tinned copper fittings	35
III STEEL / IRON.....	36
1 Galvanised steel.....	36
2 Carbon steel	38
3 Cast iron	39
4 Stainless steel	40
IV PLATINGS.....	41
1 Tin plating applied by a galvanic process on the external surface	41
V PASSIVE MATERIALS.....	42

1 Introduction

Awaiting a European acceptance scheme the 4 MS co-operate concerning the convergence of their national acceptance schemes for products in contact with drinking water. The national implementation of the procedure for the acceptance of metallic materials described in Part A allows the compilation of a common Composition List for metallic materials that are accepted in all 4 MS.

Metallic materials on this common Composition List can be used for products in contact with drinking water. For the acceptance of products made of metallic materials the composition of the metallic materials have to be check for compliance with the listed materials. Further product specific tests (e.g. nickel release from chromium plated taps) for the acceptance are under consideration in some of the 4MS.

2 Compilation of a common Composition List

For the inclusion of a material onto the common Composition List the material has to be tested according to the procedure in Part A.

The primary responsibility for assessment of materials will remain at the national level making use of established processes and the expert resources available there. Thus a manufacturer may approach a national regulatory body (or its appointed agencies) for evaluation of a new material. There are obvious practical advantages for a manufacturer in the 4MS countries to work with his "home" assessment body, but he would not be required to do so. Applicants from outside the 4MS area would be free to use any of the national arrangements.

The national arrangements will continue to operate largely as at present, but instead of producing findings and recommendations for local decision, will create assessment information and proposals in a common form (Opinions). These draft opinions will be reviewed by the appropriate bodies within each of the other MS, who will offer their comments. The aim will be to achieve agreement on where and how a material is listed and on any restrictions or other information that should be included in the listing.

3 Structure of the Composition List (see Part A 3.2)

The Composition List contains different categories of metallic materials.

A Category is defined as:

a group of materials with the same characteristics in respect of their field of application, behaviour in contact with drinking water and restrictions with regard to water composition and/or surface area.

The Composition List contains the categories' range of compositions. A material falling within a category has to be tested individually for its acceptance on the list.

Each category has one reference material.

A Reference Material is defined as:

a material falling within a category for which the characteristics of metal release into drinking water are known and reproducible, the composition is strictly controlled and the elements of interest will be at or near the upper limit of acceptability. Possible effects of some constituents to inhibit the metal release have to be taken into account.

Under each category commercially available metallic materials accepted for use in PDW will be listed. The materials may only be used for certain products due to the restrictions with respect to the surface area (Table 1).

Table 1: Product groups for metallic materials

Product Group	Examples of products or parts of products	Assumed contact surface “a”
A	Pipes in buildings installation Uncoated pipelines in water supply systems	100%
B	Fittings, ancillaries in buildings installations (e.g. pump bodies, valve bodies, water meter bodies used in buildings installations)	10%
C	<ol style="list-style-type: none"> 1. Components of products of product group B (e.g. the spindle of a pump or the moving parts in water meter in building installations). The sum of the surfaces in contact with drinking water of all these components has to be less than 10% of the total wetted surface of the product. 2. Fittings, ancillaries in water mains and water treatment works with permanent flow (e.g. pumps bodies, valves bodies used in water supply systems) 	1%
D	Components of fittings and ancillaries in water mains in water treatment works (C2)	

4MS Composition List of accepted metallic materials

I Copper alloys

1 Copper-zinc alloys

1.1 Category

Constituents (% (m/m)):

Cu	Zn
≥ 57.0%	Remainder

Impurities (% (m/m)):

Al	Fe	Ni	Pb	Sn
≤ 0.1%	≤ 0.5%	≤ 0.2%	≤ 0.2%	≤ 0.5%

Each other impurity < 0.02%

1.2 Reference Material

Constituents (% (m/m)):

Cu	Zn
57.0% - 59.0%	Remainder

Impurities (% (m/m)):

Al	Fe	Ni	Pb	Sn
≤ 0.05%	≤ 0.3%	0.15% - 0.25%	0.15% - 0.25%	≤ 0.3%

Each other impurity < 0.02%

Elements for consideration in the migration water:

Cu, Ni, Pb, Zn

Most critical test water:

Test water 1 according to EN 15664-2

1.3 Accepted Alloys

1.3.1

Notation	Product groups
CW509L* (CuZn40)	B - D

* Contents of certain elements are further restricted (see below)

Constituents (% (m/m)):

Cu	Zn
59.5% - 61.5%	Remainder

Impurities (% (m/m)):

Al	Fe	Ni*	Pb*	Sn
≤ 0.05%	≤ 0.2%	≤ 0.2%	≤ 0.2%	≤ 0.2%

Each other impurity < 0.02%

Basis for acceptance

UBA opinion (23 Nov 2011)

UBA opinion (25 March 2013)

1.3.2

Notation	Product Group
CW510L* (CuZn42)	B - D

* Contents of certain elements are further restricted (see below)

Constituents (% (m/m)):

Cu	Zn
57.0% - 59.0%	Remainder

Impurities (% (m/m)):

Al	Fe	Ni*	Pb	Sn
≤ 0.05%	≤ 0.3%	≤ 0.2%	≤ 0.2%	≤ 0.3%

Each other impurity < 0.02%

Basis for acceptance

UBA opinion (23 Nov 2011)

UBA opinion (25 March 2013)

1.3.3

Notation	Product Group
CW501L-DW* (CuZn10)	C and D

* Contents of certain elements are further restricted (see below)

Constituents (% (m/m)):

Cu	Zn
89.0% - 91.0%	Remainder

Impurities (% (m/m)):

Fe	Ni*	Pb	Sn
≤ 0.05%	≤ 0.2%	≤ 0.05%	≤ 0.1%

Each other impurity < 0.02%

1.3.4

Notation	Product Group
CW506L-DW* (CuZn33)	B - D

* Contents of certain elements are further restricted (see below)

Constituents (% (m/m)):

Cu	Zn
66.0% - 68.0%	Remainder

Impurities (% (m/m)):

Fe	Ni*	Pb	Sn
≤ 0.05%	≤ 0.2%	≤ 0.05%	≤ 0.1%

Each other impurity < 0.02%

1.3.5

Notation	Product Group
CW507L-DW* (CuZn36)	B - D

* Contents of certain elements are further restricted (see below)

Constituents (% (m/m)):

Cu	Zn
63.5% - 65.5%	Remainder

Impurities (% (m/m)):

Fe	Ni*	Pb	Sn
≤ 0.05%	≤ 0.2%	≤ 0.1%	≤ 0.1%

Each other impurity < 0.02%

1.3.6

Notation	Product Group
CW508L-DW* (CuZn37)	B - D

* Contents of certain elements are further restricted (see below)

Constituents (% (m/m)):

Cu	Zn
62.0% - 64.0%	Remainder

Impurities (% (m/m)):

Al	Fe	Ni*	Pb	Sn
≤ 0.05%	≤ 0.1%	≤ 0.2%	≤ 0.1%	≤ 0.1%

Each other impurity < 0.02%

Basis for acceptance

UBA opinion (13 March 2016)

2 Copper-zinc-aluminum alloys

2.1 Category

Constituents (% (m/m)):

Cu	Zn	Al
≥ 57.0%	Remainder	0.1% - 0.3%

Impurities (% (m/m)):

Fe	Pb	Sn
≤ 0.3%	≤ 0.2%	≤ 0.3%

2.2 Reference Material

Constituents (% (m/m)):

Cu	Zn	Al
57.0% - 59.0%	Remainder	0.1% - 0.2%

Impurities (% (m/m)):

Fe	Pb	Sn
≤ 0.3%	0.15% - 0.25%	≤ 0.3%

Each other impurity < 0.02%

Elements for consideration in the migration water:

Al, Cu, Pb, Zn

Most critical test water:

Test water 1 according to EN 15664-2

2.3 Accepted Alloys

2.3.1

Notation	Product groups
CuZn42Al	B - D

Constituents (% (m/m))

Cu	Zn	Al
57.0% - 59.0%	Remainder	0.1% - 0.3%

Impurities (% (m/m))

Fe	Pb	Sn
≤ 0.3%	≤ 0.2%	≤ 0.3%

Each other impurity < 0.02%

Basis for acceptance

UBA opinion (16 March 2015)

3 Copper-zinc-aluminum-tin alloys

3.1 Category

Constituents (% (m/m)):

Cu	Zn	Al	Sn
≥ 62.0%	Remainder	0.5% - 2.0%	0.3% - 1.0%

Impurities (% (m/m)):

Fe	Mn	Ni	Pb	Si
≤ 0.5%	≤ 0.1%	≤ 0.3%	≤ 0.2%	≤ 0.2%

3.2 Reference Material

Constituents (% (m/m)):

Cu	Zn	Al	Sn
64.0% - 66.0%	Remainder	1.40% - 1.50%	0.66% - 0.70%

Impurities (% (m/m)):

Fe	Mn	Ni	Pb	Si
≤ 0.10%	≤ 0.10%	0.06% - 0.10%	0.15% - 0.25%	≤ 0.2%

Each other impurity < 0.02%

Elements for consideration in the migration water:

Al, Cu, Ni, Pb, Zn

Most critical test water:

Test water 1 according to EN 15664-1

3.3 Accepted Alloys

3.3.1

Notation	Product groups
CuZn35Al1.5Sn	B - D

Constituents (% (m/m))

Cu	Zn	Al	Sn
64.0% - 66.0%	Remainder	1.40% - 1.60%	0.50% - 0.70%

Impurities (% (m/m))

Fe	Mn	Ni	Pb	Si
≤ 0.10%	≤ 0.10%	≤ 0.10%	≤ 0.2%	≤ 0.2%

Basis for acceptance

UBA opinion (24 Feb 2017)

4 Copper-zinc-arsenic alloys

4.1 Category

Constituents (% (m/m)):

Cu	Zn	As
≥ 61.0%	Remainder	0.02% - 0.15%

Impurities (% (m/m)):

Al	Fe	Mn	Ni	Pb	Sn
≤ 0.1%	≤ 0.5%	≤ 0.1%	≤ 0.3%	≤ 0.2%	≤ 0.5%

Each other impurity < 0.02%

4.2 Reference Material

Constituents (% (m/m)):

Cu	Zn	As
61.5% - 63.5%	Remainder	0.10% - 0.15 %

Impurities (% (m/m)):

Al	Fe	Mn	Ni	Pb	Sn
≤ 0.1%	≤ 0.1%	≤ 0.1%	0.21% - 0.35%	0.15% - 0.25%	≤ 0.1%

Each other impurity < 0.02%

Elements for consideration in the migration water:

As, Cu, Ni, Pb, Zn

Most critical test water:

Test water 1 according to EN 15664-2

4.3 Accepted Alloys

4.3.1

Notation	Product groups
CW511L (CuZn38As)	B - D

Constituents (% (m/m)):

Cu	Zn	As
61.5% - 63.5%	Remainder	0.02% - 0.15%

Impurities (% (m/m)):

Al	Fe	Mn	Ni	Pb	Sn
≤ 0.05%	≤ 0.1%	≤ 0.1%	≤ 0.3%	≤ 0.2%	≤ 0.1%

Each other impurity < 0.02%

Basis for acceptance

UBA opinion (28 March 2013)

5 Copper-zinc-arsenic-aluminium alloys

5.1 Category

Constituents (% (m/m)):

Cu	Zn	As	Al
≥ 61.0%	Remainder	0.02% - 0.15%	0.2% - 1.0%

Impurities (% (m/m)):

Fe	Mn	Pb	Sn
≤ 0.5%	≤ 0.1%	≤ 0.2%	≤ 0.3%

Each other impurity < 0.02%

5.2 Reference Material

Constituents (% (m/m)):

Cu	Zn	As	Al
63.0% - 64.5%	Remainder	0.11% - 0.14%	0.2% - 0,4%

Impurities (% (m/m)):

Fe	Mn	Pb	Sn
≤ 0.3%	≤ 0.1%	0.15% - 0.25%	≤ 0.3%

Each other impurity < 0.02%

Elements for consideration in the migration water:

Al, As, Cu, Pb, Zn

Most critical test water:

Test water 1 according to EN 15664-2

5.3 Accepted Alloys

5.3.1

Notation	Product groups
CuZn35Al-C	B - D

Constituents (% (m/m)):

Cu	Zn	As	Al
63.0% - 64.5%	Remainder	0.04% - 0.14%	0.2% - 0.7%

Impurities (% (m/m)):

Fe	Mn	Pb	Sn
≤ 0.3%	≤ 0.1%	≤ 0.2%	≤ 0.3%

Each other impurity < 0.02%

Basis for acceptance

UBA-opinion (29 July 2014)

6. Copper-zinc-arsenic-antimony-aluminum alloys

6.1 Category

Constituents (% (m/m)):

Cu	Zn	As	Sb	Al
≥ 60.0%	Remainder	0.02% - 0.10%	0.02% - 0.10%	0.02% - 1.0%

Impurities (% (m/m)):

Fe	Mn	Ni	Pb	Sn
≤ 0.5%	≤ 0.1%	≤ 0.2%	≤ 0.2%	≤ 0.5%

6.2 Reference Material

Constituents (% (m/m)):

Cu	Zn	As	Sb	Al
62.0% - 65.0%	Remainder	0.03% - 0.04%	0.04% - 0.05%	0.45% - 0.58%

Impurities (% (m/m)):

Fe	Mn	Ni	Pb	Sn
≤ 0.2%	≤ 0.1%	0.12% - 0.20%	0.15% - 0.25%	≤ 0.3%

Each other impurity < 0.02%

Elements for consideration in the migration water:

Al, As, Cu, Ni, Pb, Sb, Zn

Most critical test water:

Test water 1 according to EN 15664-2

6.3 Accepted Alloys

6.3.1

Notation	Product groups
CC771S (CuZn38AsSb)	B - D

Constituents (% (m/m))

Cu	Zn	As	Sb	Al
62.0% - 65.0%	Remainder	0.02% - 0.04%	0.02% - 0.05%	0.45% - 0,7%

Impurities (% (m/m))

Fe	Mn	Ni	Pb	Sn
≤ 0.2%	≤ 0.1%	≤ 0.20%	≤ 0.2%	≤ 0.3%

Each other impurity < 0.02%

Basis for acceptance

UBA opinion (10 July 2015)

7 Copper-zinc-lead alloys

7.1 Category

Constituents (% (m/m)):

Cu	Zn	Pb
≥ 57.0%	Remainder	0.2% - 3.5%

Impurities (% (m/m)):

Al	Fe	Ni	Si	Sn
≤ 0.3%	≤ 0.5%	≤ 0.2%	≤ 0.2%	≤ 0.5%

Each other impurity < 0.02%

7.2 Reference Material

Constituents (% (m/m)):

Cu	Zn	Pb
57.0% - 59.0%	Remainder	1.9% - 2.2%

Impurities (% (m/m)):

Al	Fe	Ni	Si	Sn
≤ 0.2%	≤ 0.3%	0.05% - 0.15%	≤ 0.03%	≤ 0.3%

Each other impurity < 0.02%

Elements for consideration in the migration water:

Cu, Ni, Pb, Zn

Most critical test water:

Test water 1 according to EN 15664-2

7.3 Accepted Alloys

7.3.1

Notation	Product groups
CW617N* (CuZn40Pb2) CW612N* (CuZn39Pb2)	B - D

* Contents of certain elements are further restricted (see below)

Constituents (% (m/m)):

Cu	Zn	Pb*
57.0% - 60.0%	Remainder	1.6% - 2.2%

Impurities (% (m/m)):

Al	Fe	Ni*	Si	Sn
≤ 0.05%	≤ 0.3%	≤ 0.1%	≤ 0.03%	≤ 0.3%

Each other impurity < 0.02%

Basis for acceptance

German Co-normative Research Report RG_CPDW_01_074

Dossier John Nuttall (March 2006)

7.3.2

Notation	Product groups
CW614N* (CuZn39Pb3) CW603N* (CuZn36Pb3)	C and D

* Contents of certain elements are further restricted (see below)

Constituents (% (m/m)):

Cu	Zn	Pb
57.0% - 62.0%	Remainder	2.5% - 3.5%

Impurities (% (m/m)):

Al	Fe	Ni*	Si	Sn
≤ 0.05%	≤ 0.3%	≤ 0.2%	≤ 0.03%	≤ 0.3%

Each other impurity < 0,02%

Basis for acceptance

German Co-normative Research Report RG_CPDW_01_074
Dossier John Nuttall (March 2006)

8 Copper-zinc-lead-aluminium alloys

8.1 Category

Constituents (% (m/m)):

Cu	Zn	Pb	Al
≥ 57.0%	Remainder	0.2% - 1.5%	0.2% - 1.0%

Impurities (% (m/m)):

Fe	Mn	Ni	Si	Sn
≤ 0.5%	≤ 0.05%	≤ 0.2%	≤ 0.05%	≤ 0.5%

Each other impurity < 0.02%

8.2 Reference Material

Constituents (% (m/m)):

Cu	Zn	Pb	Al
58.0% - 63.0%	Remainder	1.2% - 1.4%	0.3% - 0.6%

Impurities (% (m/m)):

Fe	Mn	Ni	Si	Sn
≤ 0.3%	≤ 0.05%	0.15% - 0.25%	≤ 0.05%	≤ 0.5%

Each other impurity < 0.02%

Elements for consideration in the migration water:

Al, Cu, Ni, Pb, Zn

Most critical test waters:

Test water 1 and 2 according to EN 15664-2

8.3 Accepted Alloys

8.3.1

Notation	Product groups
CC757S*(CuZn39Pb1Al-C)	B - D

* Contents of certain elements are further restricted (see below)

Constituents (% (m/m)):

Cu	Zn	Pb*	Al
58.0% - 63.0%	Remainder	0.2% - 1.4%	0.3% - 0.9%

Impurities (% (m/m)):

Fe	Mn	Ni	Si	Sn
≤ 0.3%	≤ 0.05%	≤ 0.2%	≤ 0.05%	≤ 0.5%

Each other impurity < 0.02%

Basis for acceptance

UBA opinion (29 Aug 2014)

9 Copper-zinc-lead-arsenic-aluminium alloys

9.1 Category

Constituents (% (m/m)):

Cu	Zn	Pb	As	Al
≥ 61.0%	Remainder	0.2% - 2.2%	0.02% - 0.15%	0.02% - 1.0%

Impurities (% (m/m)):

Fe	Mn	Ni	Sn
≤ 0.5%	≤ 0.1%	≤ 0.2%	≤ 0.5%

Each other impurity < 0.02%

9.2 Reference Material

Constituents (% (m/m)):

Cu	Zn	Pb	As	Al
61.0% - 63.0%	Remainder	1.4% - 1.6%	0.09% - 0.13%	0.5% - 0.7%

Impurities (% (m/m)):

Fe	Mn	Ni	Sn
≤ 0.3%	≤ 0.1%	0.15% - 0.25%	≤ 0.3%

Each other impurity < 0.02%

Elements for consideration in the migration water:

Al, As, Cu, Ni, Pb, Zn

Most critical test water:

Test water 1 according to EN 15664-2

9.3 Accepted Alloys

9.3.1

Notation	Product groups
CC770S (CuZn36Pb-C)	B - D

Constituents (% (m/m)):

Cu	Zn	Pb	As	Al
62.0% - 64.0%	Remainder	0.2% - 1.6%	0.04% - 0.14%	0.5% - 0.7%

Impurities (% (m/m)):

Fe	Mn	Ni	Sn
≤ 0.3%	≤ 0.1%	≤ 0.2%	≤ 0.3%

Each other impurity < 0.02%

Basis for acceptance

UBA opinion (29 Jan 2014)

9.3.2

Notation	Product groups
CW626N (CuZn33Pb1.5AlAs)	B - D

Constituents (% (m/m)):

Cu	Zn	Pb	As	Al
64.0% - 66.0%	Remainder	1.2% - 1.7%	0.02% - 0.15%	0.8% - 1.0%

Impurities (% (m/m)):

Fe	Mn	Ni	Sn
≤ 0.3%	≤ 0.1%	≤ 0.2%	≤ 0.3%

Each other impurity < 0.02%

Basis for acceptance

UBA opinion (02 April 2013)

9.3.3

Notation	Product groups
CW625N (CuZn35Pb1.5AlAs)	B - D

Constituents (% (m/m)):

Cu	Zn	Pb	As	Al
62.0% - 64.0%	Remainder	1.2% - 1.6%	0.02% - 0.15%	0.5% - 0.7%

Impurities (% (m/m)):

Fe	Mn	Ni	Sn
≤ 0.3%	≤ 0.1%	≤ 0.2%	≤ 0.3%

Each other impurity < 0.02%

Basis for acceptance

UBA opinion (29 Jan 2014)

10 Copper-zinc-lead-arsenic-antimony-aluminum alloys

10.1 Category

Constituents (% (m/m)):

Cu	Zn	Pb	As	Sb	Al
≥ 60.0%	Remainder	0.2% - 1.1 %	0.02% - 0.10%	0.02% - 0.10%	0.02% - 1.0%

Impurities (% (m/m)):

Fe	Mn	Ni	Sn
≤ 0.5%	≤ 0.1%	≤ 0.2%	≤ 0.5%

10.2 Reference Material

Constituents (% (m/m)):

Cu	Zn	Pb	As	Sb	Al
62.0% - 65.0%	Remainder	0.9% - 1.1%	0.03% - 0.04%	0.05% - 0.06%	0.45% - 0.58%

Impurities (% (m/m)):

Fe	Mn	Ni	Sn
≤ 0.2%	≤ 0.1%	0.15% - 0.25%	≤ 0.3%

Each other impurity < 0.02%

Elements for consideration in the migration water:

Al, As, Cu, Ni, Pb, Sb, Zn

Most critical test water:

Test water 1 according to EN 15664-2

10.3 Accepted Alloys

10.3.1

Notation	Product groups
CC772S (CuZn36Pb1.5AsSbAl)	B - D

Constituents (% (m/m))

Cu	Zn	Pb	As	Sb	Al
62.0% - 65.0%	Remainder	0.2% - 1.1%	0.02% - 0.04%	0.03% - 0.06%	0.45% - 0,7%

Impurities (% (m/m))

Fe	Mn	Ni	Sn
≤ 0.2%	≤ 0.1%	≤ 0.2%	≤ 0.3%

Each other impurity < 0.02%

Basis for acceptance

UBA opinion (29 Aug 2014)

11 Copper-zinc-lead-arsenic-aluminium-silicon alloys

11.1 Category

Constituents (% (m/m)):

Cu	Zn	Pb	As	Al	Si
≥ 61.0%	Remainder	0.2% - 1.0%	0.02% - 0.10%	0.02% - 1.0%	0.02% - 0.5%

Impurities (% (m/m)):

Fe	Mn	Ni	Sn
≤ 0.5%	≤ 0.1%	≤ 0.2%	≤ 0.5%

Each other impurity < 0.02%

11.2 Reference Material

Constituents (% (m/m)):

Cu	Zn	Pb	As	Al	Si
64.0% - 67.0%	Remainder	0.60% - 0.65%	0.07% - 0.08%	0.1% - 0.25%	0.1% - 0.2%

Impurities (% (m/m)):

Fe	Mn	Ni	Sn
≤ 0.3%	≤ 0.1%	0.15% - 0.25%	≤ 0.3%

Each other impurity < 0.02%

Elements for consideration in the migration water:

Al, As, Cu, Ni, Pb, Zn

Most critical test water:

Test water 1 and 2 according to EN 15664-2

11.3 Accepted Alloys

11.3.1

Notation	Product groups
CW725R*(CuZn33Pb1AlSiAs)	B - D

* Contents of certain elements are further restricted (see below)

Constituents (% (m/m)):

Cu	Zn	Pb*	As	Al	Si
64.0% - 67.0%	Remainder	0.4% - 0.6%	0.04% - 0.08%	0.1% - 0.4%	0.1% - 0.3%

Impurities (% (m/m)):

Fe	Mn	Ni	Sn
≤ 0.3%	≤ 0.1%	≤ 0.2%	≤ 0.3%

Each other impurity < 0.02%

Basis for acceptance

UBA opinion (27 July 2014)

12 Copper-tin-zinc-lead-nickel alloys

12.1 Category

Constituents (% (m/m)):

Cu	Sn	Zn	Pb	Ni
Remainder	4.0% - 13.0%	4.0% - 6.5%	0.2% - 3.0%	0.1% - 0.6%

Impurities (% (m/m)):

Fe	P	S	Sb
≤ 0.30%	≤ 0.04%	≤ 0.04%	≤ 0.10%

Each other impurity < 0.02%

12.2 Reference Material

Constituents (% (m/m)):

Cu	Sn	Zn	Pb	Ni
Remainder	4.0% - 4.2%	5.7% - 6.0%	2.8% - 3.0%	0.5% - 0.6%

Impurities (% (m/m)):

Fe	P	S	Sb
≤ 0.30%	≤ 0.04%	≤ 0.04%	0.09% - 0,15%

Each other impurity < 0.02%

Elements for consideration in the migration water:

Cu, Ni, Pb, Sb, Zn

Most critical test water:

Test water 1 according to EN 15664-2

12.3 Accepted Alloys

12.3.1

Notation	Product groups
CC499K* (CuSn5Zn5Pb2-C)	B - D

* Contents of certain elements are further restricted (see below)

Constituents (% (m/m)):

Cu	Sn	Zn	Pb*	Ni*
84.0% - 88.0%	4.0% - 6.0%	4.0% - 6.0%	0.2% - 3.0%	0.1% - 0.60%

Impurities (% (m/m)):

Fe	P	S	Sb
≤ 0.30%	≤ 0.04%	≤ 0.04%	≤ 0.10%

Each other impurity < 0.02%

Basis for acceptance

German Co-normative Research Report RG_CPDW_01_074

Dossier John Nuttall (March 2006)

13 Copper-tin-zinc-phosphorous-sulphur alloys

13.1 Category

Constituents (% (m/m)):

Cu	Sn	Zn	P	S
Remainder	3.0% - 9.0%	1.0% - 5.0%	0.01% - 1.0%	0.2% - 0.7%

Impurities (% (m/m)):

Fe	Ni	Pb	Sb
≤ 0.3%	≤ 0.3%	≤ 0.2%	≤ 0.1%

13.2 Reference Material

Constituents (% (m/m)):

Cu	Sn	Zn	P	S
Remainder	4.6% - 5.0%	1.0% - 3.0%	0.01% - 0.06%	0.52% - 0.65%

Impurities (% (m/m)):

Fe	Ni	Pb	Sb
≤ 0.3%	0.21% - 0.35%	0.15% - 0.25%	0.09% - 0,15%

Elements for consideration in the migration water:

Cu, Ni, Pb, Sb, Zn

Most critical test water:

Test water 1 according to EN 15664-1

13.3 Accepted Alloys

13.3.1

Notation	Product groups
CuSn4Zn2PS	B - D

Constituents (% (m/m)):

Cu	Sn	Zn	P	S
90.0% - 96.0%	3.0% - 5.0%	1.0% - 3.0%	0.01% - 0.1%	0.2% - 0.6%

Impurities (% (m/m)):

Fe	Ni	Pb	Sb
≤ 0.3%	≤ 0.3%	≤ 0.2%	≤ 0.1%

Basis for acceptance

UBA opinion (13 Feb 2017)

14 Copper-zinc-silicon-phosphorous alloys

14.1 Category

Constituents (% (m/m)):

Cu	Zn	Si	P
60.0% - 80.0%	Remainder	0.5% - 5.5%	0.01% - 0.3%

Impurities (% (m/m)):

Al	Fe	Mn	Ni	Pb	Sn
≤ 0.1%	≤ 0.5%	≤ 0.05%	≤ 0.2%	≤ 0.1%	≤ 0.5%

Each other impurity < 0.02%

14.2 Reference Material

Constituents (% (m/m)):

Cu	Zn	Si	P
75.0% - 77.0%	Remainder	2.7% - 3.0%	0.02% - 0.06%

Impurities (% (m/m)):

Al	Fe	Mn	Ni	Pb	Sn
≤ 0.05%	≤ 0.3%	≤ 0.05%	0.15% - 0.25%	0.09% - 0.15%	≤ 0.3%

Each other impurity < 0.02%

Elements for consideration in the migration water:

Cu, Ni, Pb, Zn

Most critical test water:

Test water 1 according to EN 15664-2

14.3 Accepted Alloys

14.3.1

Notation	Product groups
CW724R (CuZn21Si3P)	B - D

Constituents (% (m/m)):

Cu	Zn	Si	P
75.0% - 77.0%	Remainder	2.7% - 3.5%	0.02% - 0.10%

Impurities (% (m/m)):

Al	Fe	Mn	Ni	Pb	Sn
≤ 0.05%	≤ 0.3%	≤ 0.05%	≤ 0.2%	≤ 0.1%	≤ 0.3%

Each other impurity < 0.02%

Basis for acceptance

UBA opinion (24 Feb 2012)

14.3.2

Notation	Product groups
CC768S (CuZn21Si3P)	B - D

Constituents (% (m/m)):

Cu	Zn	Si	P
75.0% - 77.0%	Remainder	2.7% - 3.5%	0.02% - 0.10%

Impurities (% (m/m)):

Al	Fe	Mn	Ni	Pb	Sn
≤ 0.05%	≤ 0.3%	≤ 0.05%	≤ 0.2%	≤ 0.1%	≤ 0.3%

Each other impurity < 0.02%

The content of boron and zirconium has to be less than 0.02%.

Basis for acceptance

UBA opinion (09 Jan 2014)

15 Copper-silicon-zinc-manganese-phosphorous alloys

15.1 Category

Constituents (% (m/m)):

Cu	Si	Zn	Mn	P
≥ 80.0%	0.5% - 5.5%	Remainder	0.01% - 0.2%	0.01% - 0.3%

Impurities (% (m/m)):

Al	Fe	Ni	Pb	Sn
≤ 0.3%	≤ 0.5%	≤ 0.1%	≤ 0.1%	≤ 0.5%

Each other impurity < 0.02%

15.2 Reference Material

Constituents (% (m/m)):

Cu	Si	Zn	Mn	P
Remainder	2.5% - 3.5%	8.0% - 10.0%	0.03% - 0.09%	0.05% - 0.10%

Impurities (% (m/m)):

Al	Fe	Ni	Pb	Sn
≤ 0.3%	≤ 0.3%	0.06% - 0.10%	0.06% - 0.10%	≤ 0.3%

Each other impurity < 0.02%

Elements for consideration in the migration water:

Cu, Mn, Ni, Pb, Zn

Most critical test water:

Test water 1 according to EN 15664-2

15.3 Accepted Alloys

15.3.1

Notation	Product groups
CC245E (CuSi4Zn4MnP-C)	B - D

Constituents (% (m/m)):

Cu	Si	Zn	Mn	P
Remainder	2.5% - 4.5%	1.0% - 7.0%	0.03% - 0.09%	0.05% - 0.15%

Impurities (% (m/m)):

Al	Fe	Ni	Pb	Sn
≤ 0.3%	≤ 0.3%	≤ 0.10%	≤ 0.10%	≤ 0.3%

Each other impurity < 0.02%

15.3.2

Notation	Product groups
CC246E (CuSi4Zn9MnP-C)	B - D

Constituents (% (m/m)):

Cu	Si	Zn	Mn	P
Remainder	2.5% - 4.5%	7.0% - 11.0%	0.03% - 0.09%	0.05% - 0.15%

Impurities (% (m/m)):

Al	Fe	Ni	Pb	Sn
≤ 0.3%	≤ 0.3%	≤ 0.10%	≤ 0.10%	≤ 0.3%

Each other impurity < 0.02%

15.3.3

Notation	Product groups
CuSi4Zn4MnP	B - D

Constituents (% (m/m)):

Cu	Si	Zn	Mn	P
Remainder	2.5% - 4.5%	1.0% - 7.0%	0.01% - 0.09%	0.05% - 0.15%

Impurities (% (m/m)):

Al	Fe	Ni	Pb	Sn
≤ 0.3%	≤ 0.3%	≤ 0.10%	≤ 0.10%	≤ 0.3%

Each other impurity < 0.02%

15.3.4

Notation	Product groups
CuSi4Zn9MnP	B - D

Constituents (% (m/m)):

Cu	Si	Zn	Mn	P
Remainder	2.5% - 4.5%	7.0% - 11.0%	0.01% - 0.09%	0.05% - 0.15%

Impurities (% (m/m)):

Al	Fe	Ni	Pb	Sn
≤ 0.3%	≤ 0.3%	≤ 0.10%	≤ 0.10%	≤ 0.3%

Each other impurity < 0.02%

Basis for acceptance

UBA opinion (08 Jan 2016)

16 Copper-tin-phosphorous alloys

16.1 Category

Not defined

16.2 Reference Material

CW453K (CuSn 8) was accepted only for product group C on basis of a scientific dossier. For the acceptance of this material or another material belonging to this category for product group A or B a complete test according to EN 15664-1 with all three test waters according to EN 15664-2 is required. A reference material will be defined when a material is accepted for product group A or B.

16.3 Accepted Alloys

Notation	Product group
CW453K (CuSn8)	C and D

Constituents (% (m/m))

Cu	Sn	P
Remainder	7.5% - 8.5%	0.02% -0.4%

Impurities (% (m/m))

Fe	Ni	Zn
≤ 0.1%	≤ 0.2%	≤ 0.2%

Basis for acceptance

UBA opinion (31 Aug 2017)

17 Copper-tin-lead-phosphorous alloys

17.1 Category

Constituents (% (m/m)):

Cu	Sn	Pb	P
Remainder	9.0% - 13.0%	0.2% - 1.0%	0.01% - 1.0%

Impurities (% (m/m)):

Fe	Mn	Ni	S	Sb	Zn
≤ 0.2%	≤ 0.2%	≤ 0.2%	≤ 0.05%	≤ 0.1%	≤ 0.5%

17.2 Reference Material

Constituents (% (m/m)):

Cu	Sn	Pb	P
Remainder	10.6% - 11.0%	0.84% - 1.0%	0.01% - 0.10%

Impurities (% (m/m)):

Fe	Mn	Ni	S	Sb	Zn
≤ 0.2%	≤ 0.1%	0.15% - 0.25%	≤ 0.05%	0.09% - 0.15%	≤ 0.5%

Elements for consideration in the migration water:

Cu, Ni, Pb, Sb, Zn

Most critical test water:

Test water 1 according to EN 15664-1

17.3 Accepted Alloys

17.3.1

Notation	Product groups
CuSn10-C*	B - D

* Contents of certain elements are further restricted (see below)

Constituents (% (m/m)):

Cu	Sn	Pb	P
88.0% - 90.0%	9.0% - 11.0%	0.2% - 1.0%	0.01% - 0.2%

Impurities (% (m/m)):

Fe	Mn	Ni*	S	Sb*	Zn
≤ 0.2%	≤ 0.10%	≤ 0.2%	≤ 0.05%	≤ 0.1%	≤ 0.5%

Basis for acceptance

UBA opinion (13 Feb 2017)

18. Copper alloys for product group D

In addition to the materials listed for the Product Groups A, B and C for components of the Product Group D further copper alloys can be used.

The copper alloys have to comply with:

- Cu, Zn, Si, Sn, P: no restrictions
- Al, Fe, Mn: max. 3.0% (m/m)
- Pb: max. 3.5% (m/m)
- Ni: max. 3.0% (m/m)
- As, Sb: max: 0.25% (m/m)

All other: max. 0.1% (m/m)

II Coppers

1 Copper

1.1 Category

Constituents (% (m/m)):

Cu	P
≥ 99.9%	≤ 0.04%

Impurities (% (m/m)):

Others total
≤ 0.1%

Each impurity < 0.02%

1.2 Reference Material

CW024A (CU-DHP)

Elements for consideration in the migration water:

None: No need for comparative testing

1.3 Accepted Alloys

1.3.1

Notation	Product groups
CW024A (Cu-DHP)	A -D

Constituents (% (m/m)):

Cu	P
≥ 99.9%	0.015% - 0.04%

1.3.2

Notation	Product group
Cu-ETP (CW004A)	C and D

Constituents (% (m/m)):

Cu	O*
≥ 99.90%	≤ 0.040%

* Oxygen has a technological function in the material, it is not possible to specify a minimum content

1.3.3

Notation	Product groups
Cu-OF (CW008A)	B - D

Constituents (% (m/m)):

Cu
≥ 99.95%

1.3.4

Notation	Product groups
Cu-PHC (CW020A)	B - D

Constituents (% (m/m)):

Cu	P
≥ 99.95%	0.001% - 0.006%

1.3.5

Notation	Product groups
Cu-HCP (CW021A)	B - D

Constituents (% (m/m)):

Cu	P
≥ 99.95%	0.002% - 0.007%

1.3.6

Notation	Product groups
Cu-DLP (CW023A)	B - D

Constituents (% (m/m)):

Cu	P
≥ 99.90%	0.005% - 0.013%

Basis for acceptance

UBA opinion (15 May 2017)

Restrictions for the use of metallic materials with respect to water composition (health based)

The formation of the copper compounds on the surface of copper pipes and consequently the dissolution is strongly influenced by minor components of the water composition. In some water compositions, the rate of leaching of copper may be unacceptably high. Member States may need to offer guidance to the water industry and to suppliers and installers of copper pipe on restrictions that may need to be introduced on use of copper pipe in water compositions where excessive leaching of copper might occur.

Further research into the compatibility of copper with certain compositions of water needs to be carried out using harmonised procedures for investigation and evaluation.

Basis for acceptance

Research results and practical experience in several Member States are needed to characterise the conditions for safe use.

Note

The contamination of drinking water by copper pipes depends on several characteristics of water composition. There is no consensus view on their combined action and interaction at this time. In particular, there is inadequate information on the range of compositions of drinking water where non-compliance with the DWD is likely to occur.

2 Tinned copper pipes and tinned copper fittings

For tinned copper tubes and tinned copper fittings as base material copper according to 1 is used. On this substrate material a tin layer is deposited by different processes. By diffusion of copper ions into the tin layer the formation of an increasing intermetallic phase consisting of tin and copper (η -phase = Cu_6Sn_5) is formed.

2.1 Category

Constituents of the tin layer (% (m/m)):

Sn + Cu
≥ 99.90%

Impurities of the tin layer (% (m/m)):

As	Bi	Cd	Cr	Ni	Pb	Sb
≤ 0.01%	≤ 0.01%	≤ 0.01%	≤ 0.01%	≤ 0.01%	≤ 0.01%	≤ 0.01%

2.2 Reference Material

CW024A (CU-DHP)

2.3 Accepted Alloys

Notation	Product groups
CW024A (Cu-DHP) with a tin layer thickness of 1 μm	A-D

Constituents of the tin layer (% (m/m)):

Sn	Cu
> 90%	< 10%

Impurities of the tin layer (% (m/m)):

As	Bi	Cd	Cr	Ni	Pb	Sb
≤ 0.01%	≤ 0.01%	≤ 0.01%	≤ 0.01%	≤ 0.01%	≤ 0.01%	≤ 0.01%

Basis for acceptance

1. Leaching tests:
 - a. Rig tests in representative German drinking waters, published: A. Baukloh, S. Priggemeyer, U. Reiter, B. Winkler, Chemically inner tinned Copper Pipes, Less Copper in Corrosive Drinking Waters, Metall 10-11 (1998) 592 - 600.
 - b. Rig tests according to DIN 50931 (rig test): Technical report DVGW/TZW, 2000
2. Already existing approvals without restrictions in drinking waters
 - a. Netherlands: according to BRL-K19005,
 - b. Germany: according to DIN 50930, T6 and DVGW GW 392
 - c. Denmark, ETA

III Steel / Iron

1 Galvanised steel

1.1 Category

Constituents of the zinc coating (% (m/m)):

Zn

Impurities of the zinc coating (% (m/m)):

As	Bi	Cd	Cr	Pb	Sb
≤ 0.02%	≤ 0.01%	≤ 0.01%	≤ 0.02%	≤ 0.05%	≤ 0.01%

1.2 Reference Material

Not defined

1.3 Accepted Alloys

Notation	Product groups
Galvanised steel	A-D

Constituents of the zinc coating (% (m/m)):

Zn

Impurities of the zinc coating (% (m/m)):

As	Bi	Cd	Cr	Pb	Sb
≤ 0.02%	≤ 0.01%	≤ 0.01%	≤ 0.02%	≤ 0.05%	≤ 0.01%

Guidance on restrictions for the use of metallic materials with respect to water composition

The following formula is proposed as a means identifying water compositions where corrosion rates for galvanised steel is acceptable.

- pH ≥ 7.5 or free CO₂ ≤ 0.25 mmol/L
- AND Alkalinity ≥ 1.5 mmol/L
- AND S₁ < 2 (*definition of S₁ below*)
- AND Calcium ≥ 0.5 mmol/L
- AND Conductivity ≤ 600 μS/cm at 25°C
- AND S₂ < 1 or S₂ > 3 (*definition of S₂ below*)

$$S_1 = \frac{c(\text{Cl}^-) + c(\text{NO}_3^-) + 2 c(\text{SO}_4^{2-})}{c(\text{HCO}_3^-)} \text{ concentrations in mmol/l}$$

$$S_2 = \frac{c(\text{Cl}^-) + 2 c(\text{SO}_4^{2-})}{c(\text{NO}_3^-)} \text{ concentrations in mmol/l}$$

Basis for acceptance

There are regulations with respect to water composition in France (DTU 60.1 / NF P 40-201) and in Germany (DIN 50930-3). These limits are based on practical experience but are expressed in different ways. The proposal covers mainly the same water compositions as both regulations. The proposal takes into account available results from research in Germany and co-normative research.

The proposal incorporates also the recommendations given EN 12502-3 with regard to the risk of localised corrosion. This localised corrosion frequently leads to deterioration in water quality as a result of corrosion products of iron.

The proposal is based on results that have been obtained with galvanised steel pipes with lead concentrations between 1.0% and 0.6% in the zinc layer, assuming a similar behaviour of pipes with lower lead concentrations.

2 Carbon steel

Carbon Steel for pipes and tanks

Carbon steel without permanent protective layers is not suitable for use in contact with drinking water.

Carbon Steel for ancillaries

Unprotected carbon steel can be used for specific applications (e.g. pumps, valves) and only for small surface in contact with water.

2.1 Category

Not defined

2.2 Reference Material

Not defined

2.3 Accepted Alloys

Notation	Product groups
Carbon Steel according to EN 10025 / EN 10213 / EN 10222	C2

Constituents (% (m/m)):

Fe	C	Cr	Mo	Mn	Ni
	0.02% - 0.25%	0.02% - 0.30%	0.02% - 0.12%	0.02% - 1.65%	0.02% - 0.05%

Impurities (% (m/m)):

Al	Cu	Nb	P	S	Si	Ti	V
≤ 0.05%	≤ 0.55%	≤ 0.05%	≤ 0.03%	≤ 0.03%	≤ 0.6%	≤ 0.05%	≤ 0.12%

Basis for acceptance

Draft Italian Regulation

Calculation of possible impact on DW

UBA opinion (21 April 2017)

3 Cast iron

Cast iron for pipes and tanks

Cast iron without permanent protective layers is not suitable for pipes and fittings in contact with drinking water.

Cast iron for ancillaries

Unprotected cast iron can be used for specific applications (e.g. pumps, valves) and only for very small surface in contact with water. Their composition needs to be regulated.

3.1 Category

Not defined

3.2 Reference Material

Not defined

3.3 Accepted Alloys

Notation	Product groups
Cast Iron according to EN 1561 / EN 1563	C2

Constituents (% (m/m)):

Fe	C	Cu	Cr	Mo	Mn	Ni	Si
	0.02% - 4.0%	0.02% - 1.0%	0.02% - 1.0%	0.02% - 1.0%	0.02% - 1.0%	0.02% - 6.0% ¹	1.5% - 3.5%

Impurities (% (m/m)):

As	Mg	P	S	Sn	V
≤ 0.05%	≤ 0.1%	≤ 0.15%	≤ 0.1%	≤ 0.1%	≤ 0.1%

Basis for acceptance

Draft Italian Regulation

French regulation

Calculation of possible impact on DW

UBA opinion (21 April 2017)

¹ The maximum nickel content is under discussion.

4 Stainless steel

Stainless steels according to EN 10088 and EN 10283 can be applied for all product groups (A-D)

Restrictions:

Some stainless steels show a higher probability of occurrence of local corrosion (e.g. pitting or crevice corrosion) caused by the contact with certain drinking waters or in case of disinfection with high chlorine concentrations. For this purpose EN 16056 can be used to compare the passivity behaviour of the different stainless steel grades.

IV Platings

1 Tin plating applied by a galvanic process on the external surface

Components made of CW617N and CW612N (corresponding 4MS Composition List: Copper alloys / 7.3.1) CC770S (corresponding 4MS Composition List: I Copper alloys / 9.3.1) and CW625N (corresponding 4MS Composition List: I Copper alloys / 9.3.3) can be plated galvanically with a layer composition of copper and tin.

Restrictions:

- Bulk material of components to be tinned:
 - CW617N / CW612N (corresponding 4MS Composition List: I Copper alloys / 7.3.1)
 - CC770S (corresponding 4MS Composition List: I Copper alloys / 9.3.1)
 - CW625N (corresponding 4MS Composition List: I Copper alloys / 9.3.3)
- Layer composition: 1.) Cu 2.) Sn
- applied process: galvanic tin plating
- Purity of the used anodes: $\geq 99,90\%$

Additional requirement:

For the respective production process it has to be proven that the manufactured products are not contaminated with organic substances used in the galvanic process baths. This can be demonstrated by a migration test according to EN 12873-1. The evidence can be provided in the course of an approval/certification process of respective plated products. In this process a test of the metal release is not required. Additionally, a quality assurance scheme for the production process is required. In UK additional product tests might be necessary.

– V Passive materials

1 Category

Not defined

2 Reference Material

Not defined

3 Accepted Alloys

Notation	Product groups
NiCr7030	B - D

Constituents (% (m/m)):

Ni	Cr	Si
≥ 60.0%	29.0% – 32.0%	0.50% – 2.0%

Impurities (% (m/m)):

Al	C	Co	Cu	Fe	Mn	P	S
≤ 0.30%	≤ 0.10%	≤ 1.5%	≤ 0.50%	≤ 5.0%	≤ 1.00%	≤ 0.020%	≤ 0.015%

The evaluation of the material NiCr7030 is based on test results according to EN 16056. Following criterion for the passivity was applied:

$$E_{\text{pit}} > \text{free corrosion potential} + 500 \text{ mV}$$

E_{pit} : pitting potential according to EN 16056

free corrosion potential: potential at the beginning of the test (open circuit potential), which corresponds the potential of oxygen in the neutral test water

4 Further passive metallic materials for product group D

For product group D further passive metallic materials can be used in contact with drinking water. These materials do not need to be listed in this composition list.

Basis for acceptance

UBA opinion (22 February 2018)